



riva light cure

ENGLISH

LIGHT CURED RESIN REINFORCED GLASS IONOMER RESTORATIVE MATERIAL INSTRUCTIONS FOR USE

Riva Light Cure is the ideal radiopaque, resin reinforced glass ionomer restorative material. With excellent tooth adhesion, sustained fluoride release, high compressive strength and command set, Riva Light Cure is useful for a wide range of restorative applications. It is available in A1, A2, A3, A3.5, A4, B2, B3, B4, C2, C4 and bleach shades, in capsules and powder-liquid kits.

INDICATIONS FOR USE:

- Minimal Class I, II, and III restorations
- Class V restorations
- Deciduous teeth restorations
- Geriatric restorations
- Core build-ups
- Root surface restorations
- As a base or liner
- Pit and fissure sealant
- Semi-permanent fillings

INSTRUCTIONS FOR USING RIVA LIGHT CURE CAPSULES

PREPARATION:

- Clean and isolate tooth.
Note: A conservative cavity should be prepared, employing standard techniques and instruments. Undercuts are not necessary.
- In cases where pulp protection is necessary, use a calcium hydroxide liner.

CONDITIONING / ETCHING:

- Apply Riva Conditioner to the prepared surfaces and leave in cavity for 10 seconds.
- Rinse thoroughly with water.
- Remove excess water. Keep moist. Avoid contamination.

IMPORTANT: Be careful not to completely dry the surface. Surface should be glistening.

PLACEMENT PROCEDURE:

- Activate the capsule by pushing the plunger until it is flush with the body.
Important: Do not dick with applicator before you mix.
- Immediately place the capsule into the Ultramat 2 amalgamator, or any other suitable mixer (4000-4800rpm), and triturate for 10 seconds.
- Immediately remove the capsule and place into the Riva applicator.
- Click the trigger of the Riva applicator until glass ionomer paste is seen through the clear nozzle.
- Fill Riva Light Cure into the cavity, being careful not to trap air under the restoration. Note: At 23°C/74°F working time will be about 130 seconds (2'10'') from the start of mixing. In situations above this temperature, working times will shorten. Adhesion strength will decrease if material is manipulated after this time. Use a layering technique for cavities deeper than 2 mm.
- Light cure for 20 seconds using the SDI Radii LED Curing Light or any other visible light-curing device (470 nm wavelength). Place light source as closely as possible to the cement surface.

Powder/Liquid ratio (g/g)	0.42/0.14
Mixing time (min, sec.)	10 seconds
Working time (min., sec.)	2'10''
Light Curing Time (sec)	20''
Depth of Cure (A3) (mm)	1.8
Minimum delivery/capsule	0.13mL

Test conditions: temperature (23 ± 1°C), relative humidity (50 ± 10%).

ISO 9917-2 Light-activated radiopaque glass polyalkenoate cement.

Minimum net contents per capsule: 0.42g powder and 0.14g (0.12mL) liquid.

- Finish the restoration using standard techniques. Finishing may be commenced immediately after light curing.
- Instruct patient not to eat for at least one hour after procedure.

INSTRUCTIONS FOR USING RIVA LIGHT CURE POWDER / LIQUID KITS

PREPARATION:

- Clean and isolate tooth.
Note: A conservative cavity should be prepared, employing standard techniques and instruments. Undercuts are not necessary.
- In cases where pulp protection is necessary, use a calcium hydroxide liner.

CONDITIONING / ETCHING:

- Apply Riva Conditioner to the prepared surfaces and leave in cavity for 10 seconds.

OR

Apply Super Etch 37% Phosphoric Acid to the prepared surfaces and leave in cavity for 5 seconds.

- Rinse thoroughly with water.
- Remove excess water. Keep moist. Avoid contamination.

IMPORTANT: Be careful not to completely dry the surface. Surface should be glistening.

MIXING OF LIQUID AND POWDER:

Powder-liquid dosage:	1 flat scoop to 2 drops
Powder-liquid ratio:	0.22g/0.07g (3.1:1)
Recommended mixing time:	30 secs.
Light Curing Time (sec)	20''
Depth of Cure (A3) (mm)	1.8

Test conditions: temperature (23 ± 1°C), relative humidity (50 ± 10%).

ISO 9917-2 Light-activated radiopaque glass polyalkenoate cement. Mixing pad type: non-absorbent paper or glass slab

NOTE: Cool glass slab for extended working time. Avoid condensation.

- Gently tap Riva Light Cure powder jar on the hand.
- Dispense one level measure of powder onto the mixing pad/glass slab. Replace cap tightly.
- Dispense two drops of liquid onto the mixing pad/glass slab next to the powder. Quickly replace cap tightly.
- Divide the powder into two equal parts.
- Mix the liquid with one part of the powder for 10 seconds using a plastic spatula, then include the second part and mix for another 15 to 20 seconds.

PLACEMENT PROCEDURE

- Place Riva Light Cure into the cavity, being careful not to trap air under or within the restoration.

Note: At 23°C/74°F working time will be about 120 seconds (2'00''). In situations above this temperature, working times will shorten. Adhesion strength will decrease if material is manipulated after this time. Use a layering technique for cavity deeper than 2 mm.

- Light cure for 20 seconds using the SDI Radii LED Curing Light or any other visible light-curing device (470 nm wavelength). Place light source as closely as possible to the cement surface.

- Finish restoration using standard techniques. Finishing may be commenced immediately after light curing.

- Instruct patient not to eat for at least one hour after procedure.

- Exposure to strong lights during mixing and placement can reduce working time.

STORAGE AND SHELF LIFE

Do not remove Riva Light Cure capsules from their foil packets until ready to use.

Store at temperatures between 4°C - 20°C (39°F - 68°F) for capsules and 4°C - 25°C (39°F - 77°F) for powder/liquid kits.

Use at room temperature between 20°C and 25°C (68°F - 77°F).

PRECAUTIONS:

For professional use only.

Keep out of reach of children.

The above-mentioned products may cause skin irritations to some people. In such cases, discontinue use and seek medical attention.

Do not take internally.

Do not inject SDI Riva products.

Do not mix powder or liquid with any other brand of glass ionomer products.

Caution: Federal Law restricts this device to sale by or on the order of a dentist.

SDS available at www.sdi.com.au or contact your regional representative.

FIRST AID:

In case of Riva Light Cure and Riva Conditioner contact with eyes, wash thoroughly with water and seek medical attention.

In case of contact with skin, remove using a cloth or sponge soaked in alcohol.

AVAILABLE SHADES: A1, A2, A3, A3.5, A4, B2, B3, B4, C2, C4, Bleach

PACKAGING

- 50 Capsule Boxes
- Assorted Capsule Box: 10 each of shade A1, A2, A3, A3.5, B2
- Powder Liquid Kits : 8g (7.2mL) Liquid Bottle, 15g Powder Jar, accessories
- 8g (7.2mL) Liquid Bottle Refill
- 15g Powder Jar Refill

Made in Australia by SDI Limited

Bayswater, Victoria 3153

Australia 1 800 337 003

Austria 00800 0225 5734

Brazil 0800 770 1735

France 00800 0225 5734

Germany 0800 1005759

Ireland 00800 0225 5734

Italy 00800 0225 5734

New Zealand 0800 734 034

Spain 00800 0225 5734

United Kingdom 00800 0225 5734

USA & Canada 1 800 228 5166

www.sdi.com.au



SDI Germany GmbH

Hansestrasse 85

51149 Cologne

Germany

T+49 2203 9255 0



20°C
68°F
4°C
39°F
capsule



25°C
77°F
4°C
39°F
powder/liquid

Last Revision: 2017-01

PAK41115 M